




Technical parameter	Standard	Unit	Result
Construction			heterogeneous
Total thickness	mm	EN ISO 24346	2.0
Wear layer thickness	mm	EN ISO 24340	0.7
Length of rolls	lm	EN ISO 24341	20
Width	m	EN ISO 24341	2
Total weight	kg/m ²	EN ISO 23997	2.7
Residual indentation	max. mm	EN ISO 24343	0.1
Dimensional stability	max.%	EN ISO 23999	±0.2
Curling	max.mm	EN ISO 23999	8
Fire resistance	class	EN 13501-1	C _{fl} -s1
	class	DIN 4102/ ÖNORM	B1
Abrasion group	group	MSZ EN 660-1	T
Abrasion resistance	max.m	MSZ EN 423	<250
Light fastness	grade	EN ISO 105-B02	> 6
Chemical resistance		EN ISO 26987	✓
Slip resistance	class	EN 13893	DS
Castor chair resistance		EN 425	✓
Flexibility (diameter 20/40mm)	visual evaluation	MSZ EN 435	✓
Surface treatment			CLP
Antibacterial and fungicid treatment			graboSAN
Enviromental attributes			Solvent and heavy metal free product
CE MARKING	EN 14041		✓